

Cleaning Instructions:

X-Static® Cubicle Laundering Instructions:

- Load Fabric into washer (Do Not Overload).
- Use the usual hospital protocol (rinse, drain, etc.), for washing cubicles and note maximum temperature of 160°F
- Detergent must be non-ionic (with cloud point above 160°F) with a maximum pH not to exceed 10.
- Oxidative **bleaching agents should not be used** as these will damage X-Static silver antimicrobial fiber. These include sodium, hypochlorite, hydrogen peroxide, and per(oxy)acetic acid (PAA).
- A thorough rinse is essential to remove traces of surfactant, as residual detergent will adversely affect the X-Static silver antimicrobial.
- Do not overload washer or dryer.
- Fabric softeners should not be used.
- Always ensure that the fabric is thoroughly dried with heat. The dryer exhaust temperature should not exceed 160°F.
- Washers and dryers should be inspected regularly to ensure there are no rough spots that could damage the fabric.
- As is the usual procedure with laundering synthetic cubicle curtains, after the dry cycle is complete, curtains should be quickly removed to avoid over exposure to the heat drying cam.
- Silver is a natural element and may tarnish. This does not affect the biocidal properties of the material.
- Always process one single cubicle first before processing bulk cubicles. A thorough examination & evaluation of the test cubicle should be reviewed to make sure that the proper results are attained.

For any questions, please contact our Technical Department:

ACTech@arc-com.com or 1-800-223-5466 x4882

List of Incompatible Chemicals for Use With X-Static Silver Antimicrobial Fiber

The Table below contains a general list of chemicals that are incompatible for use with X-Static filament or staple fibers. While this list is not comprehensive, it does reference the most common chemicals used in processing, dyeing, finishing and laundering that are incompatible with the X-Static technology.

Incompatible Chemicals	Effect on X-Static Silver Antimicrobial Fiber	Impact on End-Use Requirement	Recommended Substitutes
Sulfur Powder	Sulfur degrades X-Static	<ul style="list-style-type: none"> • Potential issue with consistency of color, luster • Potential issue with reduction in thermal and electrical properties 	<ul style="list-style-type: none"> • Non-sulfur powder-containing chemicals • Non-sulfur-containing atmosphere (that is, away from high vehicle exhaust areas)
Ammonium Sulfide	Sulfur containing compounds degrade X-Static	<ul style="list-style-type: none"> • Potential issue with consistency of color, luster • Potential issue with reduction in thermal and electrical properties 	<ul style="list-style-type: none"> • Non-ammonium sulfide-containing chemicals
Sodium Hypochlorite (Household Bleach)	Sodium hypochlorite degrades X-Static	<ul style="list-style-type: none"> • Potential issue with consistency of color, luster • Potential issue with reduction in thermal and electrical properties 	<ul style="list-style-type: none"> • Non hypochlorite-containing cleaning agents
Chlorine Gas	Chlorine degrades X-Static	<ul style="list-style-type: none"> • Potential issue with consistency of color, luster • Potential issue with reduction in thermal and electrical properties 	<ul style="list-style-type: none"> • Non-hypochlorite-containing cleaning agents
All Strong Acids	Strong acids degrade, dissolve and oxidize X-Static	<ul style="list-style-type: none"> • Potential issue with consistency of color, luster • Potential issue with reduction in thermal and electrical properties 	<ul style="list-style-type: none"> • Alternate process that does not expose X-Static to strong acids
Strong Oxidizing Agents	Strong oxidizing agents, degrade, dissolve and oxidize X-Static	<ul style="list-style-type: none"> • Potential issue with consistency of color, luster • Potential issue with reduction in thermal and electrical properties 	<ul style="list-style-type: none"> • Alternate process that does not expose X-Static to strong oxidizing agents
Sodium Silicate	Sodium Silicate reacts with X-Static	<ul style="list-style-type: none"> • Visual color change • Deposits of orange yellow precipitate of silver silicate on substrate 	<ul style="list-style-type: none"> • Magnesium salts of ethylenediamine tetra acetic acid (EDTA) and tetrasodium pyrophosphate (TSPP)
Sodium Hydrosulfite (Sodium Dithionite)	Degrades X-Static and effects overall hue of fabric	<ul style="list-style-type: none"> • Potential issue with consistency of color, luster • Potential "tea stains" on finished fabric • Potential uniform change in hue (towards brown) • Potential issue with reduction in thermal and electrical properties 	<ul style="list-style-type: none"> • Non hydrosulfite reducing agents such as isopropyl alcohol